

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTa Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

EMILY
ZiZ

TEST REPORT

CEZANNE BASE CLOTH

TEST NUMBER : 7-597693-BN
ISSUE DATE : 02/06/2014
PRINT DATE : 02/06/2014
ORDER NUMBER : 27534

SAMPLE DESCRIPTION Printed chenille fabric
Nominal Composition: 100% Polyester
Nominal Thickness: 450g/m²

AS 1530.2-1993 Test for Flammability of Materials

DATE TESTED: Flammability Index: 3 Range 0 - 100 for most material

02/06/2014 Length Width

Spread Factor: Range 0 - 40	2	1
Heat Factor: Range 0 - upward	1	1
Maximum height (d)	Length	Width
mean	4.1	3.5
cv	29.0	32.7 %
Time (t)	mean	N/A
	cv	N/A %
Heat (a)	mean	2.6 degC min
	cv	59.6 %
No of specimens tested	9	9

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use

207452

1

(END OF REPORT)

PAGE 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd make no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and form of the advertisement have been approved by the Managing Director of AWTa Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTa Product Testing

A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O. Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

TEST NUMBER : 7-597693-BN
ISSUE DATE : 02/06/2014
PRINT DATE : 02/06/2014
ORDER NUMBER : 27534

SAMPLE DESCRIPTION Printed chenille fabric
Nominal Composition: 100% Polyester
Nominal Thickness: 450g/m²

AS 1530.2-1993 Test for Flammability of Materials

DATE TESTED: Flammability Index: 3 Range 0 - 100 for most material

02/06/2014 Length Width

Spread Factor: Range 0 - 40	2	1
Heat Factor: Range 0 - upward	1	1
Maximum height (d)	Length	Width
mean	4.1	3.5
cv	29.0	32.7 %
Time (t)	mean	N/A
cv	N/A	N/A %
Heat (a)	mean	2.6 degC min
cv	46.4	59.6 %
No of specimens tested	9	9

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

TEST NUMBER : 7-598160-BN
ISSUE DATE : 01/07/2014
PRINT DATE : 01/07/2014
ORDER NUMBER : 27534

SAMPLE DESCRIPTION

Printed Chenille fabric
Colour: Multicolour
Approx thickness: 1mm
End Use: Upholstery

THESE RESULTS MUST BE CONSIDERED IN CONJUNCTION
WITH THE COMMENTS ON THE FOLLOWING PAGE(S)

Material Specification provided by client:

Nominal composition: 100% Polyester
Nominal mass: 450g/m²

AS/NZS 1530.3 - 1999 Simultaneous determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

RESULTS: Face tested: Face

	Date tested:	Mean	Standard Error
Ignition time	30/06/2014	9.13	min 0.23
Flame propagation time		Nil	s Nil
Heat release integral		43.0	kJ/m ² 2.5
Smoke release, log d		-0.8866	0.0308
Optical density, d		0.1315	/m

Number of specimens ignited: 6

Number of specimens tested: 6

REGULATORY INDICES:	Ignitability Index	11	Range 0-20
	Spread of Flame Index	0	Range 0-10
	Heat Evolved Index	1	Range 0-10
	Smoke Developed Index	5	Range 0-10



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

TEST NUMBER : 7-598160-BN
ISSUE DATE : 01/07/2014
PRINT DATE : 01/07/2014
ORDER NUMBER : 27534

Comments:

These results only apply to the specimen mounted, as described in this report.

The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena, it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

Specimens tended to flash before ignition. Ignition was based on the occurrence of a single flash of flame which lasted longer than 10 seconds.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

