

AWTA PRODUCT TESTING

EMILY
ZIZ

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

MIRO BASE CLOTH

Test Number : 16-005860
Issue Date : 17/11/2016
Print Date : 17/11/2016
Order Number : 34223

Sample Description Textured printing base cloth

Colour : White

End Use : Upholstery/Drapery

Nominal Composition : 100% Polyester

Nominal Mass per Unit Area/Density : 470g/m²

AS 1530.2-1993

**Methods for Fire Tests on Building Materials, Components and Structures.
Part 2: Test for Flammability of Materials**

Date Tested 17/11/2016

Flammability Index 1

Length Width

Spread Factor 0 0

Heat Factor 1 1

Maximum height (d)

Mean 1.3 1.2

Coefficient of Variation 19.4 22.1 %

Heat (a)

Mean 1.5 1.5 °C.min

Coefficient of Variation 0.0 0.0 %

Number of Specimens 6 6
Tested

Observation Visible smoke, melting, dripping

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

76503

15915

Page 1 of 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356



Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Test Number : 16-005861
Issue Date : 30/11/2016
Print Date : 30/11/2016
Order Number : 34223

Sample Description Textured printing base cloth
Colour : White
End Use : Upholstery/Drapery

Nominal Composition : 100% Polyester
Nominal Mass per Unit Area/Density : 470g/m²
Nominal Thickness : Approx. 1mm

AS/NZS 1530.3-1999 **Methods for Fire Tests on Building Materials, Components and Structures**
Part 3: Simultaneous Determination of Ignitability,
Flame Propagation, Heat Release and Smoke Release

Face tested:	Face	
Date tested:	30/11/2016	
	Standard Error	Mean
Ignition time	0.11	10.83 min
Flame propagation time	Nil	Nil sec
Heat release integral	3.1	53.2 kJ/m ²
Smoke release, log d	0.0399	-0.7741
Optical density, d		0.1718 / metre
Number of specimens ignited:	6	
Number of specimens tested:	6	
Regulatory Indices:		
Ignitability Index	9	Range 0-20
Spread of Flame Index	0	Range 0-10
Heat Evolved Index	2	Range 0-10
Smoke Developed Index	5	Range 0-10

77738

15916

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
985

: Accreditation No.
: Accreditation No.

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated.
AWTA
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test
results
relate only to the sample or samples tested. This document shall not be reproduced except in full and
shall

2009

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Test Number : 16-005861

Issue Date : 30/11/2016

Print Date : 30/11/2016

Order Number : 34223

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Specimens tended to flash before ignition. Ignition was based on the occurrence of a single flash of flame which lasted longer than 10 seconds.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

To allow free movement of sample during testing all corners were folded away from the clamps.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

77738

15916

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
985

: Accreditation No.
: Accreditation No.

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated.
AWTA
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test
results
relate only to the sample or samples tested. This document shall not be reproduced except in full and
shall

2009

APPROVED SIGNATORY

0204/11/06



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR